

12V

100Ah

Lead Carbon

AGM

12SLR100DC

Rechargeable Lead Carbon AGM Battery

SPECIF	ICAI	10	N5
Nominal Volt	aae		

 Nominal Capacity

 10 hour rate
 (10A to 10.80V)
 100Ah

 5 hour rate
 (17A to 10.20V)
 85Ah

 1 hour rate
 (60A to 9.60V)
 60Ah

 1C
 (100A to 9.60V)
 63.3Ah

12V

14.4V to 15.0V

30A

13.5V to 13.8V

Weight Approx. 31.2kg

Internal Resistance (at 1KHz) Approx. $5m\Omega$

Maximum Discharge Current (5 secs) 600A

Charge Methods at 25°C

Cyclic Use
Charging Voltage

Coefficient -5.0mV/°C/Cell

Maximum Charging Current

Standby Use

Float Charging Voltage Coefficient -3.0mV/°C/Cell

Operating Temperature Range

 Charge
 −15°C to 40°C

 Discharge
 −15°C to 50°C

 Storage
 −15°C to 40°C

Charge Retention (Shelf Life) at 20°C

 1 month
 98%

 3 months
 94%

 6 months
 85%

Case Material ABS UL94 HB

Termination F8 (M6 Bolt)

Description of Torque Value of Hardware for the Terminals

Recommended Torque Value Max. Allowable Torque Value

Classified as a non-spillable battery. Approved for transportation by:

- Air (IATA/ICAO provision A67)
- Road

Barcode

• Sea (per IMDG Special Provision 238)

M6: 7 N-m (71kgf-cm) M6: 10 N-m (102kgf-cm)










DIMENSIONS

mm (inch)












CHARACTERISTICS CHARTS

Relationship Between Temperature and Charging Voltage



FEATURES & BENEFITS

- Industry leading 99.99% pure lead content for superior service life and dependable performance.
- Lead Carbon negative plate for better partial SOC performance and reduced sulphation meaning longer service life.
- Enhanced charge acceptance for quicker energy recovery best suited to renewable energy systems.
- Maintenance free technology and non-spillable design.
- Extremely low self discharge characteristics.
- Manufactured by Kung Long Battery (KLB) at facilities in Taiwan and Vietnam. KLB is a leading manufacturer and complies with relevant international quality standards including ISO9001, CE ETL9000, UL1989, OHSAS18001 and ISO17025. KLB supports Green Sustainable supply chain practices.












Effect of Temperature on Capacity 25°C(77°F)







Aug2025

Performance may vary depending on application. All specifications are correct at time of creation. All specifications and operation conditions contained in this datasheet are subject to change or improvement without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data. For clarification and updated information, please contact us.