

RECHARGEABLE LITHIUM IRON PHOSPHATE BATTERY

IFR12-1200-Y (12.8V 121.6Ah)

Standard Model

SPECIFICATIONS	
Nominal Voltage	12.8V
Nominal Capacity @5hr Rate	121.6Ah
Watt-hour	1556.5Wh
Dimensions	
Length	328 mm
Width	172 mm
Height	212mm
Weight	13.7±0.3kg
Internal Resistance (at 1KHz)	≤45mΩ
Charge @25°C	
Standard Charge Current	≤20A
Maximum Charge Current	50A
Cut-off Voltage	14.4 ±0.15V
Discharge @25°C	
Standard Discharge Current	80A
Max. Continuous Discharge	80A-100A (≤5min)
Cut-off Voltage	About 10.0V
Assembly	26650 - 4S32P
Operating Temp	
Charge	0 - +45°C
Discharge	-20 - +60°C
Storage	0 - +40°C
Humidity	RH≤85%
Case Material	ABS
Termination	M8 Bolt
Fuel Gauge	N/A
Communications Port	N/A

BUILT IN PROTECTION

All Drypower Rechargeable Lithium batteries adhere to strict safety guidelines by incorporating Battery Management Systems (BMS) that include protection components such as:

Protection: Overcharge protection, over discharge protection, over temperature protection, over current protection, balancing function

- Integrated Circuit (IC) Thermistor
- MOSFET • Fuse
- Protection Circuit Module (PCM)

The BMS in each Drypower battery helps to:

- 1. Maintain safety for users.
- 2. Prevent damage to equipment and property.
- 3. Eliminate concerns about use of the wrong type of charger.
- 4. Minimise the risk of overdischarge causing damaging.
- 5. Provide short circuit and overcharge protection.



Drypower Rechargeable Lithium (LiFePO4) batteries offer unmatched performance in a wide range of industrial or high drain applications.


With its impressive cycle life of up to 2000 cycles, implementing Drypower batteries drastically reduces overall total cost of ownership compared to SLA batteries.

DIMENSIONS













Discharge Voltage Profiles @ 0.5C Discharge Rate

Various Ambient Temperatures




Discharge Capacity Performance

Charged: 0.5C to 14.6V, CV@14.6 to 1A Discharged: 0.5C to 10.5V




Discharge Voltage Profiles @ Various Temperatures





Typical Voltage Profiles & SOC Profiles @ 0.5C Charging

23°C Ambient Temperatures



FEATURES & BENEFITS



High cycle life

>2000 cycles @80% DoD for effectively lower total cost of ownership.



Lightweight

Drypower Lithium batteries provide more Wh/Kg while also being up to 1/3 the weight of its SLA equivalent.



Built in circuit protection

Battery Management Systems (BMS) are incorporated to maintain safety and prevent damage.



Better storage

12-18+ months thanks to its extremely low self discharge (LSD) rate and no risk of sulphation.



Quickly recharge

Save time and increase productivity with less down time thanks to superior charge/discharge efficiency.



Extreme heat tolerance

Suitable for use in a wider range of applications where ambient temperature is unusually high: up to $+60^{\circ}$ C.



Longer service life

Low maintenance batteries with stable chemistry. Easily monitor state of health (SoH) of smart models.

SUITABLE APPLICATIONS

Lithium Iron Phosphate can be used in any application that would normally use Lead Acid, GEL or AGM type batteries*. LiFePO4 in 4S = 12.8V and 8S = 25.6V is closest to Lead Acid equivalents of the lithium rechargeable types.

Suitable applications include caravan, marine, golf carts & buggies, solar storage, remote monitoring, switching applications and more.

*Exceptions may apply so please consult with a Drypower technical expert for more information regarding your application.

CAUTIONS

- Do NOT short circuit, crush or disassemble.
- Do NOT heat or incinerate.
- Do NOT immerse in any liquid.
- Only use a Drypower approved LiFePO4 charger.
- Store at 50% capacity. Recharge every 3 months. The storage area should be clean, cool, dry and ventilated.

Performance may vary depending on application. All specifications are correct at time of creation. All specifications and operation conditions contained in this datasheet are subject to change or improvement without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data. For clarification and updated information, please contact us.